

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 10016-4 (1984): Methods of Test for Polybutadiene Rubbers, Part 4: Determination of CIS, Trans and Vinyl Structure [PCD 13: Rubber and Rubber Products]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 10016 (Part 4) - 1984

Indian Standard

**METHODS OF TEST FOR
POLYBUTADIENE RUBBERS**

**PART 4 DETERMINATION OF CIS, TRANS AND
VINYL STRUCTURE**

UDC 678.762.2 : 543.871



© Copyright 1984

INDIAN STANDARDS INSTITUTION
BHAKT BHAVAN, 9 BHADUR SHAH ZAFAR MARG
NEW DELHI 110002

*Indian Standard***METHODS OF TEST FOR
POLYBUTADIENE RUBBERS****PART 4 DETERMINATION OF CIS, TRANS AND
VINYL STRUCTURE**

Rubber Sectional Committee, PCDC 14

Chairman

SHRI LALIT MOHAN JAMNADAS

Representing

Cosmos India Rubber Works Pvt Ltd, Bombay

Vice-Chairman

SHRI S. B. GANGULI

Dunlop India Ltd, Calcutta

SHRI K. S. LOGANATHAN (*Alternate*)*Members*

SHRI O. P. AGARWAL

Trans Asia Carpets Ltd, Sikandrabad

SHRI J. N. JHA (*Alternate*)

SHRI A. K. BANDYOPADHAYAY

Ministry of Defence (DGI)

SHRI V. BHATTACHARYA (*Alternate*)

DR B. BANERJEE

Carbon and Chemicals India Ltd, Calcutta

DR D. BANERJEE

Escon Consultants Pvt Ltd, Calcutta

DR P. S. BHARGAVA

Alkali and Chemicals Corporation of India Ltd,
CalcuttaSHRI N. C. SAMAJDAR (*Alternate*)

SHRI J. CHATTERJEE

Andrew Yule & Co Ltd, Calcutta

SHRI A. K. BISWAS (*Alternate*)

DR D. K. DAS

National Test House, Calcutta

SHRI A. GHOSH (*Alternate*)

SHRI P. B. G. DASTIDAR

Bata India Ltd, Calcutta

SHRI S. SARKAR (*Alternate*)

SHRI S. L. GANDHI

Ministry of Defence (R & D)

SHRI H. C. PERTI (*Alternate*)

SHRI J. M. GARG

Directorate General of Technical Development

SHRI A. GEORGE JOHN

Madras Rubber Factory Ltd, Madras

SHRI K. J. JOSEPH

Plantation Corporation of Kerala Ltd, Kottayam

SHRI K. T. VARGHESE (*Alternate*)(*Continued on page 2*)

© Copyright 1984

INDIAN STANDARDS INSTITUTION

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
SHRI G. R. KAVISHVAR	Indian Rubber Regenerating Co Ltd, Thane
SHRI P. S. VIRANI (<i>Alternate</i>)	
SHRI N. S. KHANNA	All India Rubber Industries Association, Bombay
SHRI R. R. PANDIT (<i>Alternate</i>)	
SHRI K. N. KOSHY	M. M. Rubber Co Ltd, Madras
SHRI N. SUBRAMANIAN (<i>Alternate</i>)	
SHRI P. K. MADHAVA MENON	Thirumbadi Rubber Co Ltd, Mookkam
SHRI D. W. MCCRIRICK	Association of Planters of Kerala, Kottayam
SHRI P. K. MENON (<i>Alternate</i>)	
SHRI P. K. MENON	United Planters' Association of Southern India, Coonoor
SHRI E. B. UNNI (<i>Alternate</i>)	
DR W. MILLNS	Indian Rubber Manufacturers Research Association, Thane
SHRI N. B. FEGADE (<i>Alternate</i>)	
SHRI R. MURLEEDHARAN NAIR	Hindustan Latex Ltd, Bangalore
SHRI R. R. PANDIT	Bayer (India) Ltd, Bombay
SHRI D. J. BHARUCHA (<i>Alternate</i>)	
SHRI S. A. PASHA	London Rubber Co (India) Ltd, Madras
SHRI R. KRISHNAN (<i>Alternate</i>)	
SHRI M. C. PAUL	Arakkunnam Co-operative Rubber Marketing Society Ltd, Arakkunnam
SHRI K. S. RADHAKRISHNAN	National Rubber Manufacturers Ltd, Calcutta
SHRI R. P. MATHUR (<i>Alternate</i>)	
DR S. B. RATH	Synthetics and Chemicals Ltd, Bombay
SHRI H. C. CHOPRA (<i>Alternate</i>)	
DR R. V. REDDY	State Trading Corporation of India Ltd, New Delhi
SHRI O. P. ARORA (<i>Alternate</i>)	
SHRI S. V. SARMA	Travancore Rubber & Tea Co Ltd, Trivandrum
SHRI C. S. KRISHNASWAMY (<i>Alternate</i>)	
SHRI K. C. SEKAR	Padinjarekara Agencies Ltd, Kottayam
SHRI P. C. SENGUPTA	Indian Tyre Manufacturers Association, New Delhi
SHRI SUNIL I. SHAH	Indian Petrochemicals Corporation Ltd, Vadodara
SHRI A. K. MALLIK (<i>Alternate</i>)	
SHRI E. V. THOMAS	Rubber Research Institute of India, Kottayam; and Rubber Board, Kottayam
DR M. G. KUMARAN (<i>Alternate</i>)	
SHRI M. S. SAXENA, Director (P & C)	Director General, ISI (<i>Ex-officio Member</i>)

Secretary

SHRI A. KAR
Senior Deputy Director (P & C), ISI

(Continued on page 8)

Indian Standard

METHODS OF TEST FOR POLYBUTADIENE RUBBERS

PART 4 DETERMINATION OF CIS, TRANS AND VINYL STRUCTURE

0. FOREWORD

0.1 This Indian Standard (Part 4) was adopted by the Indian Standards Institution on 10 September 1984, after the draft finalized by the Rubber Sectional Committee had been approved by the Petroleum, Coal and Related Products Division Council.

0.2 In this series, methods of test for polybutadiene rubbers are given. Various other methods of test for polybutadiene rubbers are covered in the following parts:

- Part 1 Method of taking out test portions from sample bales
- Part 2 Determination of ash
- Part 3 Determination of antioxidants
- Part 5 Determination of gel content

0.3 Test methods for the following characteristics are similar to those for styrene butadiene rubbers and the methods indicated below shall be used in these cases:

Volatile matter	SBR : 1 and SBR : 2 of IS : 4518 (Part 1)-1967*;
Mooney viscosity	SBR : 8 of IS 4518 (Part 1)-1967*;
Solvent extract	SBR : 9 of IS : 4518 (Part 2)-1971*;
Oil content	SBR : 10 of IS : 4518 (Part 2)-1971*.

*Methods of tests for styrene-butadiene rubbers (SBR) :

Part 1 Determination of volatile matter, total ash, organic acid, soap, antioxidants, bound styrene and mooney viscosity (*Reaffirmed* 1979).

Part 2 Determination of solvent extract and oil content.

0.4 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard (Part 4) prescribes the method of determining the relative amounts of various unsaturated forms in polybutadiene rubbers.

2. QUALITY OF REAGENTS

2.1 Unless specified otherwise, pure chemicals and distilled water (*see* IS : 1070-1977†) shall be employed in tests.

NOTE — 'Pure chemicals' shall mean chemicals that do not contain impurities which affect the results of analysis.

3. OUTLINE OF METHOD

3.1 A film of rubber is cast from dichloromethane or benzene or carbon tetrachloride (CCl_4) solution on to a potassium bromide prism and an infrared spectrum obtained from the film in the region from 9 to 16 microns (1200 to 600 cm^{-1}). The cis, trans and vinyl concentration are calculated from peaks appearing at 13.6 microns to 13.8 microns (793.6 to 735 cm^{-1}) for cis, at 10.35 microns (965 cm^{-1}) for trans and at 10.95 microns (910 cm^{-1}) for vinyl.

4. APPARATUS

4.1 Infrared Spectrophotometer

4.2 Conical Flask 50 ml

4.3 Potassium Bromide Prism

4.4 Mechanical Shaker

4.5 Analytical Balance

4.6 Prism Holder

4.7 Desiccator — Containing suitable drying agent.

5. REAGENTS

5.1 Dichloromethane, Benzene or Carbon Tetrachloride — Spectroscopic grade.

*Rules for rounding off numerical values (*revised*).

†Specification for water for general laboratory use (*second revision*).

6. PROCEDURE

6.1 Weigh accurately about 2.5 g of dry finished rubber taken in accordance with 2 of IS : 10016 (Part 1)-1981*. Cut the rubber into small cubes of about 0.3 mm size. Place the rubber in the conical flask; add 28 ml of dichloromethane or benzene or carbon tetrachloride. Place the flask on a mechanical shaker for 6 to 8 hours. Flask should be tightly closed to avoid evaporation.

6.2 Adjust zero and hundred percent transmittance on the infrared spectrophotometer.

6.3 Remove the potassium bromide prism from the dessicator. Add several drops of cement from the conical flask to the centre of the prism. Tilt the prism to 45° angle and let excess cement run off. Let the prism dry for about 10 to 15 minutes at 45° angle. The thickness of the film so formed should be uniform. Carefully place the prism into the aluminium holder with film outward. With the function switch set at stop, manually move the pen carriage slowly past the 13 microns to 14 micron lines on the chart and observe whether the cis peak is recorded between 0.7 to 1.0 in the absorption graph. Move the pen carriage slowly back to approximately the 8 micron line, lower the pen and move the function switch to start. The instrument will now make the desired scan from 8 micron to 16 micron when it will shut itself off.

6.4 Remove the prism from the holder and carefully remove the rubber film by rubbing gently with tissue paper. Remove the chart paper from the bed and use it for the calculation.

7. CALCULATION

7.1 Draw a perpendicular line through the trans peak appearing at 10.35 microns (965 cm^{-1}), another line through vinyl peak 10.95 microns (910 cm^{-1}) and a third line through the cis peak appearing at 13.6 microns to 13.8 microns (793.6 to 735 cm^{-1}).

7.2 The base line for vinyl peak 10.95 microns (910 cm^{-1}) and for cis peak 13.6 microns to 13.8 microns (793.6 to 735 cm^{-1}) will be the same.

7.3 With a french curve, carefully draw the curve line which represents the reference base line correction for the trans absorption at about 10.35 microns (965 cm^{-1}) and at about 10.95 microns (910 cm^{-1}) for vinyl absorption. The point where the curve line crosses the perpendicular line serves as the reference base line for calculating the trans absorption and vinyl absorption.

*Methods of test for polybutadiene rubber : Part 1 Method of taking out test portions from sample bales.

7.3.1 For information a representative curve obtained from the standard infrared spectrophotometer is shown in Fig. 1.




FIG. 1 REPRESENTATIVE CURVE FROM STANDARD INFRARED SPECTROPHOTOMETER

7.4 Calculate the relative concentration of the three components as follows:

$$C_o = 1 \times \text{cis peak}$$

$$C_t = 0.118 \times \text{trans peak}$$

$$C_v = 0.164 \times \text{vinyl peak}$$

$$\text{Cis percent by mass} = \frac{C_o \times 100}{C_o + C_t + C_v}$$

$$\text{Trans percent by mass} = \frac{C_t \times 100}{C_o + C_t + C_v}$$

$$\text{Vinyl percent by mass} = \frac{C_v \times 100}{C_o + C_t + C_v}$$

NOTE — Factors 0.118 and 0.164. These factors are derived from a certified standard of high Cis-Polybutadiene.

(Continued from page 2)

Methods of Testing Subcommittee, PCDC 14 : 1

<i>Convener</i>	<i>Representing</i>
DR S. N. CHAKRAVARTY	Modi Rubber Ltd, Modipuram
<i>Members</i>	
SHRI S. K. MUSTAFI (<i>Alternate to</i> Dr S. N. Chakravarty)	
SHRI P. S. BALASUBRAMANIAM	L. G. Balakrishnan & Brothers Ltd, Coimbatore
SHRI J. CHATTERJEE	Andrew Yule & Co Ltd, Calcutta
SHRI A. K. BISWAS (<i>Alternate</i>)	
SHRI P. K. CHATTERJEE	Bayer (India) Ltd, Bombay
SHRI K. J. JANAKAR (<i>Alternate</i>)	
DR C. K. DAS	National Rubber Manufacturers Ltd, Calcutta
SHRI R. P. MATHUR (<i>Alternate</i>)	
SHRI J. M. GARG	Directorate General of Technical Development, New Delhi
SHRI G. R. KAVISHVAR	Indian Rubber Regenerating Co Ltd, Bombay
SHRI P. S. VIRANI (<i>Alternate</i>)	
SHRI PULIN L. KINARIWALA	The Cosmos India Rubber Works Pvt Ltd, Bombay
SHRI S. N. GHADGE (<i>Alternate</i>)	
SHRI K. S. LOGANATHAN	Dunlop India Ltd, Calcutta
DR S. CHATTOPADHYAY (<i>Alternate</i>)	
SHRI P. K. MADHAVA MENON	The Thirumbadi Rubber Co Ltd, Mookam
SHRI A. K. MALLIK	Indian Petrochemicals Corporation Ltd, Vadodara
DR Y. N. SHARMA (<i>Alternate</i>)	
DR W. MILLNS	Indian Rubber Manufacturers Research Associ- ation, Thane
SHRI R. MURALEEDHARAN NAIR	Hindustan Latex Ltd, Trivandrum
SHRI P. L. NAG	Ministry of Defence (DGI)
SHRI H. L. SRIVASTAVA (<i>Alternate</i>)	
SHRI P. K. PAIN	National Test House, Calcutta
DR S. B. RATH	Synthetics & Chemicals Ltd, Bombay
SHRI H. C. CHOPRA (<i>Alternate</i>)	
SHRI S. V. SARMA	Travancore Rubber & Tea Co Ltd, Trivandrum
SHRI C. S. KRISHNASWAMY (<i>Alternate</i>)	
SHRI K. C. SEKAR	Padinjarekara Agencies Ltd, Kottayam
SHRI E. V. THOMAS	Rubber Board, Kottayam
SHRI V. G. TORSEKAR	Polyolefins Industries Ltd, Bombay
SHRI V. K. SUD (<i>Alternate</i>)	